

ชื่อเรื่องการค้นคว้าแบบอิสระเชิงวิทยานิพนธ์

การเตรียมลีเชี่ยนให้เคลือบเซรามิกและ
การใช้งาน

ชื่อผู้เขียน

นางสาวนิโอลล์ ชีวะลดาพร
สาขาวิชาการล้อนเคมี

วิทยาศาสตร์มหาบัณฑิต

คณะกรรมการสอนการค้นคว้าแบบอิสระเชิงวิทยานิพนธ์

ผู้ช่วยศาสตราจารย์ ดร. โภคล สาระเวก

ประธานกรรมการ

รองศาสตราจารย์ ดร. กานุจนา แก้วกำเนิด

กรรมการ

รองศาสตราจารย์ ดร. ประศักดิ์ ถาวรยุติการท์

กรรมการ

บทคัดย่อ

การศึกษานี้มีวัตถุประสงค์ในการเตรียมลีเชี่ยนให้เคลือบเซรามิก จากสารเคมีบางชนิด เพื่อใช้เขียนในงานเครื่องปั้นดินเผา ซึ่งเตรียมได้โดยการขัดผลลัพธ์ การเผาลังเคราะห์สี การบดละเมียด การล้าง ลีเชี่ยน พร้อมทั้งศึกษาอิทธิพลของเคลือบพื้นฐานบางชนิดว่าจะมีผลต่อลีเชี่ยนให้เคลือบที่เตรียมได้อย่างไร

จากการศึกษาพบว่าล้วนผลลัพธ์ของลีเชี่ยนให้เคลือบที่ให้ลีสวายงาม เมื่อใช้กับเคลือบชนิดไอล์ม์เกรช มีดังนี้ ลีแดงประกอบด้วย SnO_2 40 % CaCO_3 40 % SiO_2 20 % K_2CrO_4 3 % เผาลังเคราะห์สีที่อุณหภูมิ 1150 °ช. ลีม่วงประกอบด้วย Cr_2O_3 4.7 % CaCO_3 9.4 % SiO_2 9.4 % SnO_2 76.5 % เผาลังเคราะห์สีที่อุณหภูมิ 1300 °ช. ลีเหลืองประกอบด้วย ZrO_2 67.8 % SiO_2 32.8 % Pr_6O_{11} 6 % NaF 3 % NH_4Cl 4 % เผาลังเคราะห์สีที่อุณหภูมิ 1250 °ช. ลีล้มประกอบด้วย TiO_2 88.5 % Sb_2O_3 8.9 % $\text{K}_2\text{Cr}_2\text{O}_7$ 2.6 % เผาลังเคราะห์สีที่อุณหภูมิ 1150-

1300 °ช., สีน้ำเงินปะกอนด้วย CoO 1 โมล Al_2O_3 1 โมล เผาสังเคราะห์สีที่อุณหภูมิ 1200 °ช., สีเขียวปะกอนด้วย TiO_2 33.3 % Sb_2O_3 33.3 % Cr_2O_3 33.4 % เผาสังเคราะห์สีที่อุณหภูมิ 1150 °ช., สีฟ้าปะกอนด้วย ZrO_2 67 % SiO_2 33 % V_2O_5 3 % NaCl 12 % NH_4Cl 6 % เผาสังเคราะห์สีที่อุณหภูมิ 1250-1300 °ช., สีน้ำตาลปะกอนด้วย Fe_2O_3 34 % Cr_2O_3 34 % ZnO 32 % เผาสังเคราะห์สีที่อุณหภูมิ 800-1300 °ช.

ลิขสิทธิ์มหาวิทยาลัยเชียงใหม่
Copyright © by Chiang Mai University
All rights reserved

Research Title Preparation of Ceramic Underglaze Pigments
and Their Applications

Author Miss Nilobon Cheevasathaporn

M.S. Teaching Chemistry

Examining Committee :

Assist.Prof.Dr.Kosol Sarawek

Chairman

Assoc.Prof.Dr.Kanchana Keowkamnerd

Member

Assoc.Prof.Dr.Prasak Thavornyutikarn

Member

A b s t r a c t

Ceramic underglaze pigments prepared from some chemical agents and used for pottery decoration were studied. The preparation technique was mixing, calcination, grinding and washing. In addition, the influence of some basic glaze which was affected underglaze pigments was investigated.

It was found that the underglaze pigments were fit for lime glaze. The best red pigment was consisted of 40 % SnO_2 , 40 % CaCO_3 , 20 % SiO_2 and 3 % K_2CrO_4 and calcined at 1150 °C. The best violet pigment was consisted of 4.7 % Cr_2O_3 , 9.4 % CaCO_3 , 9.4 % SiO_2 and 76.5 % SnO_2 and calcined at 1300 °C. The constitute of yellow pigment was 67.2 % ZrO_2 , 32.8 % SiO_2 ,

6 % Pr_6O_{11} , 3 % NaF, 4 % NH_4Cl and was calcined at 1250 °C. The composition of orange pigment was 88.5 % TiO_2 , 8.9 % Sb_2O_3 , 2.6 % $\text{K}_2\text{Cr}_2\text{O}_7$ and was calcined at 1150 - 1300 °C. The blue pigment was consisted of 1 mol CoO , 1 mol Al_2O_3 and calcined at 1200 °C. The composition of green pigment was 33.3 % TiO_2 , 33.3 % Sb_2O_3 , 33.4 % Cr_2O_3 and was calcined at 1150 °C. The constitute of light blue pigment was 67 % ZrO_2 , 33 % SiO_2 , 3 % V_2O_5 , 12 % NaCl, 6 % NH_4Cl and was calcined at 1250-1300 °C. The brown pigment was consisted of 34 % Fe_2O_3 , 34 % Cr_2O_3 , 32 % ZnO and calcined at 800-1300 °C.