

## TABLE OF CONTENTS

	<b>Page</b>
<b>ACKNOWLEDGEMENTS</b>	iii
<b>ABSTRACT (THAI)</b>	v
<b>ABSTRACT (ENGLISH)</b>	vi
<b>LIST OF TABLES</b>	xi
<b>LIST OF FIGURES</b>	xii
<b>CHAPTER I INTRODUCTION</b>	1
Purposes of the study	2
Scope of the study	3
<b>CHAPTER II LITERATURE REVIEW</b>	4
I. Tooth surface and its preparation	5
II. Etching and priming techniques	6
1. Conventional etching (total-etching)	6
2. Self-etching	9
III. Light curing unit	11
IV. Adhesive systems	11
<b>CHAPTER III MATERIALS AND METHODS</b>	24
I. Materials	24
II. Instruments	31
III. Methods	36
1. Shear bond strength testing	36

2. Adhesive remnant evaluation	47
3. Statistical analysis	49
<b>CHAPTER IV RESULTS</b>	50
I. The statistics describing the shear bond strength values in each sample group	50
II. The comparison of mean shear bond strength in each group by analysis of variance and multiple comparisons	52
III. The frequency of adhesive remnant index scores in each group	54
<b>CHAPTER V DISCUSSION</b>	56
I. Discussion of the results of the study	57
1. Shear bond strength values	57
1.1 Non-contaminated conditions	57
1.2 Saliva-contaminated conditions	58
2. Site of adhesive failure	60
II. Discussion of the materials and methods in the study	61
1. Tooth selection	61
2. Saliva	62
3. Brackets	62
4. Force calibration	62
5. Shear bond strength test	63
6. Temperature change	63

7. Limitations of the research	64
7.1 <i>In vitro</i> study	64
7.2 Artificial saliva	64
III. Clinical implications	64
<b>CHAPTER VI CONCLUSIONS</b>	65
<b>BIBLIOGRAPHY</b>	67
<b>APPENDICES</b>	77
Appendix A	78
Appendix B	80
<b>CURRICULUM VITAE</b>	82

## LIST OF TABLES

<b>Table</b>	<b>Page</b>
1 The chemical composition of each adhesive according to the manufacturer	16
2 Previous studies on shear bond strength with orthodontic stainless steel brackets regarding contamination	19
3 The composition of artificial saliva 1,000 ml	29
4 The study design	40
5 Means ( $\bar{x}$ ), standard deviations (SD), and ranges (Min, Max) of shear bond strength for each adhesive system under non-contaminated and saliva-contaminated conditions	51
6 The normality test of the shear bond strength values	52
7 Analysis of variance (ANOVA) of mean shear bond strength	53
8 Statistical comparisons of mean shear bond strength using Tukey's test	54
9 Statistically significant differences of mean shear bond strength using Tukey's test	54
10 Chi-square test of the Adhesive Remnant Index scores of each group	55
11 The frequency of adhesive remnant index scores (percentages in parentheses) in each group	55
12 The raw data of shear bond strength in each group	78
13 The raw data of adhesive remnant index scores in each group	80

## LIST OF FIGURES

<b>Figure</b>		<b>Page</b>
1	Scanning electron micrograph showing the Type 1 etching pattern after applying phosphoric acid for 1 minute (Magnification X 1750)	7
2	Scanning electron micrograph showing the Type 2 etching pattern after applying phosphoric acid for 1 minute (Magnification X 1750)	7
3	Scanning electron micrograph showing the Type 3 etching pattern after applying phosphoric acid for 1 minute (Magnification X 1750)	8
4	Scanning electron micrograph showing the Type 4 etching pattern after applying phosphoric acid for 1 minute (Magnification X 1750)	8
5	Scanning electron micrograph showing the Type 5 etching pattern after applying phosphoric acid for 1 minute (Magnification X 1750)	9
6	Contact angle between adhesive and tooth surface	12
7	BisGMA (Bisphenol-A-glycidyl dimethacrylate)	13
8	HEMA (2-hydroxyethyl methacrylate)	13
9	PEGDMA (Polyethylene glycol dimethacrylate)	14
10	TEGDMA (Triethylene glycol dimethacrylate)	14
11	An extracted maxillary first premolar	24
12	a Metal bracket	25
12	b Base of bracket	25
13	35% Phosphoric acid	26
14	Transbond™ XT primer and Transbond™ XT Light Cure Adhesive Paste	26

15	Transbond™ Plus Self Etching Primer	27
16	Transbond™ Plus Color Change Adhesive	27
17	Beauty Ortho Bond®	28
18	Assure® total-etching system	29
19	Cylindrical polyvinylchloride ring	30
20	IsoMet® 1000	31
21	Tension and Compression Gauge	31
22	Proline® mechanical pipette	32
23	Mini LED™ light curing unit	32
24	Incubator	33
25	Thermocycling equipment	34
26	Instron® Universal Testing Machine	35
27	De-bonding plate	35
28	Mounting jig	36
29	Tooth sample embedded in clay block	37
30	The placement of light tip 5-mm away from the interproximal edges of the bracket base	41
31	Light intensity check for Mini LED™ curing unit	41
32	Flow chart of bracket bonding procedure	42
33	Sample in a polyvinylchloride ring held with a 0.016 x 0.022 inch stainless steel wire, tied with an elastomeric ligature on a 2-mm plastic plate	43
34	Sample embedded in polyvinylchloride ring with self cured acrylic resin	44

35 a	Thermocycling machine set at 2,000 cycles	44
35 b	Cold-water bath set at 5° C	44
35 c	Hot-water bath set at 55° C.	44
36	Polyvinylchloride ring mounted into the mounting jig attached to the lower pneumatic grip with the de-bonding plate attached to the upper pneumatic grip	46
37	The apparatus assembled for testing shear bond strength	46
38	Bracket base superimposed on a line grid	48
39 a	ARI Score “0”	48
39 b	ARI Score “1”	48
39 c	ARI Score “2”	48
39 d	ARI Score “3”	48
40	Diagram showing mean shear bond strength in each group	51