ชื่อเรื่องวิทยานิพนธ์

การผลิตแผ่นใยไม้อัดแข็งจากวัสคุเหลือใช้ทางการเกษตรค้วย กระบวนการระเบิดด้วยไอน้ำ

ผู้เขียน นายธีระวัฒน์ วิชัยจัทคะ

ปริญญา

วิสวกรรมศาสตรมหาบัณฑิต (วิสวกรรมอุตสาหการ)

อาจารย์ที่ปรึกษาวิทยานิพนธ์

้ผู้ช่วยศาสตราจารย์ คร.อรรถพล สมุทคุปติ๋

บทคัดย่อ

งานวิจัยนี้ศึกษาแนวทางการ ใช้ประโยชน์จากวัสดุเหลือใช้ภาคการเกษตร ที่เป็นทรัพยากร หมุนเวียนในประเทศ เพื่อ นำมาพัฒนาเป็นผลิตภัณฑ์ประเภทแผ่นใยไม้อัดแข็ง ซึ่งเป็นหนึ่งใน วัสดุ ทางเลือกที่สามารถทดแทนการ ใช้ทรัพยากรจากป่าไม้ เพื่อเป็นทางออกในการปัญหา การเสื่อม สลายอย่างรวดเร็วของทรัพยากร ธรรมชาติ และสิ่งแวดล้อม การวิจัยนี้แบ่งการศึกษาออกเป็นสอง ส่วน การศึกษาในส่วนแรกจะเป็นการ คัดเลือก ประเภทพืชที่มีศักยภาพ และเหมาะสมมากที่สุด สำหรับนำวัสดุเหลือใช้ภาคการเกษตรที่เกิดขึ้นมาพัฒนาเป็นผลิตภัณฑ์แผ่นใยไม้อัดแข็ง โดยในการ AHP เป็นเครื่องมือในการตัดสินใจ ซึ่งการวิเคราะห์ คัดเลือกจะใช้การวิเคราะห์ด้วยเทคนิค ประกอบด้วยเกณฑ์ในการ คัดเลือกตัดสินใจ 5 เกณฑ์ คือ ปริมาณผลผลิต พื้นที่เพาะปลูก ปริมาณ วัสดุเหลือใช้ที่เกิดขึ้น ราคาของวัตถุดิบ และอุปสรรคในการจัดเตรียมวัตถุดิบ ผลการศึกษาพบว่า พืชเกษตรประเภทข้าวเป็นทางเลือกที่เหมาะสมมากที่สุดสำหรับนำมาพัฒนาเป็นวัตถุดิบในการผลิต วัสดุทดแทนไม้ประเภทแผ่นใยไม้อัดแข็ง การศึกษาในส่วนที่สองคือ การผลิต และทดสอบ คุณสมบัติของแผ่นใยใม้อัดแข็ง โดยในการดำเนินงานวิจัยได้ใช้ฟางข้าวเป็นวัตถุดิบ ซึ่งเป็นวัสดุ เหลือใช้ภาคการเกษตรจากข้าวที่ได้รับเลือกจากการศึกษาในขั้นตอนแรก มาผลิตเป็นแผ่นใยไม้อัด ้แขึ่ง มีความหนาแน่นเฉลี่ยเท่ากับ 1.19 g/cm³ ผลิต โดยกระบวนการระเบิดเยื่อด้วยไอน้ำ ผลการ ทดสอบกุณสมบัติ พบว่าแผ่นใยไม้อัดแข็งที่ได้จากการระเบิดเยื่อที่ระดับความคัน 2.4 MPa ให้ คุณสมบัติของแผ่นใยไม้อัดแข็งที่ดีสุดจากระดับความดันในการทดลองทั้งหมด โดยให้มีค่าความ แข็งแรงคัดเท่ากับ 32.733 MPa มอดูลัสยืดหยุ่นเท่ากับ 13,097.83 MPa การดูดซึมน้ำเท่ากับ 37.37% และการพองตัวเมื่อแช่น้ำเท่ากับ 26.02% ส่วนการศึกษาผลกระทบทางสิ่งแวคล้อมที่เกิดขึ้นจากการ ผลิตแผ่นใยไม้อัดแข็งด้วยกรรมวิธีระเบิดเยื่อด้วยไอน้ำ พบว่ามีค่าผลกระทบต่อสิ่งแวดล้อมรวม

เท่ากับ 2.5726E-03 Pt โดยกระบวนการอัดร้อนเป็นกระบวนการที่เกิดผลกระทบต่อสิ่งแวดล้อม มากที่สุด รองลงมาคือกระบวนการระเบิดเยื่อด้วยไอน้ำ มีสัดส่วนของผลกระทบต่อสิ่งแวดล้อมจาก ทั้งสองกระบวนการร้อยละ 54.02 และ 43.14 ตามลำดับ เมื่อแยกตามประเภทของผลกระทบที่ เกิดขึ้น พบว่าผลกระทบส่วนใหญ่ที่เกิดขึ้นเป็นผลกระทบในด้านการเกิดพิษในดินที่ส่งผลต่อมนุษย์ มีค่าผลกระทบเท่ากับ 1.1979E-03 Pt คิดเป็นสัดส่วนร้อยละ 46.56 ของผลกระทบทั้งหมด เมื่อ วิเคราะห์เปรียบเทียบกับผลิตภัณฑ์ประเภทไม้ประกอบจากฐานข้อมูล LCA พบว่าแผ่นใยไม้อัดแข็ง ที่ผลิตขึ้นด้วยกรรมวิธีระเบิดเยื่อด้วยไอน้ำจะให้ค่าผลกระทบทางสิ่งแวดล้อมเท่ากับ 2.57E-03 Pt ซึ่งมีระดับผลกระทบทางสิ่งแวดล้อมสูงกว่าผลิตภัณฑ์ประเภท Fiberboard เล็กน้อย



ลิขสิทธิ์มหาวิทยาลัยเชียงใหม่ Copyright[©] by Chiang Mai University All rights reserved

Thesis Title Hardboard Production from Agricultural Residues by

Steam Explosion Process

Author Mr. Teerawat Vijaykadga

Degree Master of Engineering (Industrial Engineering)

Thesis Advisor Assistant Professor Dr. Uttapol Smutkupt

ABSTRACT

The purpose of this study was to study the way to utilize agricultural residue, the circulated resource in Thailand, by developing into fiberboard product that was one of alternative materials that could compensate the usage of forest resource. This was the way to resolve the rapid depreciation of natural resource and environment. This study was divided into two parts. The former study was the selection for the most effective and proper agricultural material to develop into fiberboard by analyzing with AHP technique, a decision making tool. The analysis was composed of five criteria; the product quantity, cultivated area, residue quantity, raw material price and the obstacle of raw material preparation. The results of the study was: Rice was the most proper agriculture residue for developing into the material for producing fiberboard. The latter study was the production and testing the specification of fiberboard. The research use rice straw to be raw material to produce fiberboard which had average density 1.19 g/cm3 by steam explosion Process. The result of specification testing were the fiberboard that process by steam explosion at pressure level 2.4 MPa gave the most excellent property when compared with other pressure levels by having modulus of rupture 32.733 MPa, modulus of elasticity was 13,097.83 MPa, water absorption was 37.37% and swelling in water was 26.02% In the part of the environmental affect from fiberboard production by steam explosion process, found that total

environmental affect value was 2.5726E-03 Pt. The compressed heating process was the most environmental affect, then was the steam explosion process. Both of process have the percentage of environmental affect were 54.02 and 43.14 by order. When separate by type of the affect, found that the most affect was human toxicity to soil that was 1.1979E-03 Pt or 46.56 of total affect. The product comparison from production by the steam explosion; Fiberboard, Medium density fiberboard, Particleboard and Woodboard under LCA database found the value of environmental affect higher than general fiberboard production a little. In the process of steam explosion gave the environmental affect value 2.57E-03 Pt.

