

<b>Thesis Title</b>	Electrical Property Development of Lead-free Barium Zirconate Titanate Ceramics		
<b>Author</b>	Mr. Parkpoom Jarupoom		
<b>Degree</b>	Doctor of Philosophy (Materials Science)		
<b>Thesis Advisory Committee</b>	Assoc. Prof. Dr. Gobwute Rujjanagul		Advisor
	Prof. Emeritus Dr. Tawee Tunkasiri		Co-advisor
	Asst. Prof. Dr. Kamonpan Pengpat		Co-advisor

### ABSTRACT

In this research project, properties of lead free barium zirconate titanate based ceramics were investigated. The barium zirconate titanate ceramics having a composition of  $\text{Ba}(\text{Zr}_{0.07}\text{Ti}_{0.93})\text{O}_3$  was selected for this study. The ceramics were prepared by a solid-state reaction technique. Effects of  $\text{B}_2\text{O}_3$  addition on many properties of  $\text{Ba}(\text{Zr}_{0.07}\text{Ti}_{0.93})\text{O}_3$  ceramics were examined. The pure and doped ceramics were annealed at various annealing times to study their relation to the ceramic properties. Finally, nano-particles of Co and Ni were added into the ceramics to form novel nanocomposites. Effects of the nano-particles on the properties of the prepared nanocomposites were studied.

For effects of  $B_2O_3$  doping, the result showed that  $B_2O_3$  addition decreased the sintering temperature by  $200^\circ C$ . The doping increased electrical properties of  $Ba(Zr_{0.07}Ti_{0.93})O_3$  ceramics where 2 wt%  $B_2O_3$  doped ceramics had the maximum  $d_{33}$  and  $g_{33}$  values about 291 pC/N and  $21 \times 10^{-3}$  Vm/N respectively. These values are quite high for the lead-free ceramics.

In case of annealed ceramics, it was observed that the annealing affected on physical and electrical properties of the pure and doped  $Ba(Zr_{0.07}Ti_{0.93})O_3$  ceramics. The experiment results showed that 8 h annealing was an optimum annealing time for improving the properties of the pure and doped ceramics. The 8 h annealed sample exhibited very high strain and  $d_{33}^*$  values of 0.47% and 603 pm/V (at 8kV/mm), respectively.

For the nanocomposites, it was found that the nano-particles increased magnetic behavior as well as mechanical properties of the samples. However, the optimum ferroelectric and magnetic properties were achieved for 0.1vol.% of the Co and Ni additions.

ชื่อเรื่องวิทยานิพนธ์	การพัฒนาสมบัติทางไฟฟ้าของเซรามิกไร้สารตะกั่ว แบเรียมเซอร์โคเนตไทเทเนต	
ผู้เขียน	นายภาคภูมิ จารุภูมิ	
ปริญญา	วิทยาศาสตรดุษฎีบัณฑิต (วัสดุศาสตร์)	
คณะกรรมการที่ปรึกษาวิทยานิพนธ์	รศ. ดร. กอบวุฒิ รุจิจนากุล ศ. เกียรติคุณ ดร. ทวี ตันขศิริ ผศ. ดร. กมลพรรณ เฟื่องพัด	อาจารย์ที่ปรึกษาหลัก อาจารย์ที่ปรึกษาร่วม อาจารย์ที่ปรึกษาร่วม

### บทคัดย่อ

ในงานวิจัยนี้ได้ทำการศึกษาสมบัติของเซรามิกแบเรียมเซอร์โคเนตไทเทเนต โดยได้เลือกทำ การศึกษาเซรามิกแบเรียมเซอร์โคเนตไทเทเนต ในองค์ประกอบ  $\text{Ba}(\text{Zr}_{0.07}\text{Ti}_{0.93})\text{O}_3$  ซึ่งผ่านการเตรียมด้วยเทคนิคปฏิกิริยาของแข็ง โดยได้ศึกษาผลกระทบจากการเจือด้วยโบรอนออกไซด์ ที่มีต่อสมบัติในด้านต่างๆของเซรามิก  $\text{Ba}(\text{Zr}_{0.07}\text{Ti}_{0.93})\text{O}_3$  จากนั้นเซรามิกบริสุทธิ์ และที่ผ่านการเจือได้ถูกอบอ่อนที่เวลาแตกต่างกัน เพื่อศึกษาถึงความสัมพันธ์ต่อสมบัติต่างๆของเซรามิก อีกทั้งอนุภาคระดับนาโนเมตรของโคบอลต์ (Co) และนิกเกิล (Ni) ได้ถูกเติมเข้าไปในเซรามิกเพื่อที่จะสร้างนาโนคอมโพสิตชนิดใหม่ขึ้นมา ผลของอนุภาคนาโนต่อสมบัติและการเตรียมของนาโนคอมโพสิตได้ถูกตรวจสอบในงานวิจัย

สำหรับผลของการเจือโบรอนออกไซด์ แสดงให้เห็นว่าจากเจือโบรอนออกไซด์ ส่งผลให้อุณหภูมิซินเตอร์มีค่าลดลง 200 องศาเซลเซียส อีกทั้งการเจือยังส่งผลต่อสมบัติทางไฟฟ้าที่เพิ่มขึ้นของ  $\text{Ba}(\text{Zr}_{0.07}\text{Ti}_{0.93})\text{O}_3$  ซึ่งเซรามิกที่ผ่านการเจือด้วยโบรอนออกไซด์ที่ปริมาณร้อยละ 2 โดยน้ำหนัก นั้นจะมีค่าสัมประสิทธิ์เพียโซอิเล็กทริก ( $d_{33}$ ) ที่สูงที่สุด และมีค่าสัมประสิทธิ์ความต่างศักย์ ( $g_{33}$ ) อยู่ที่ 291 pC/N และ  $21 \times 10^{-3}$  ตามลำดับ ซึ่งค่าดังกล่าวเป็นค่าที่สูงสำหรับเซรามิกไร้สารตะกั่ว

ในกรณีของการอบอ่อนของเซรามิกนั้น ได้ถูกตรวจสอบว่าการอบอ่อนส่งผลต่อสมบัติทางกายภาพและทางไฟฟ้าของเซรามิกบริสุทธิ์  $\text{Ba}(\text{Zr}_{0.07}\text{Ti}_{0.93})\text{O}_3$  และที่ผ่านการเจือ จากผลการทดลองแสดงให้เห็นว่าการอบอ่อนด้วยเวลา 8 ชั่วโมง เป็นเวลาการอบอ่อนที่เหมาะสมสำหรับการปรับปรุงสมบัติของเซรามิกบริสุทธิ์ และที่ผ่านการเจือ ซึ่งชิ้นงานที่ผ่านการอบอ่อนที่ 8 ชั่วโมงจะแสดงค่าของผลทางความเครียด และ  $d_{33}^*$  ที่สูงมาก ที่ 0.47% และ 603 pm/V (ที่ 8 kV/mm) ตามลำดับ

สำหรับนาโนคอมโพสิต ได้ถูกพบว่าอนุภาคนาโนสามารถเพิ่มสภาพแม่เหล็กได้ดีตลอดจนสมบัติทางกลของชิ้นงาน อย่างไรก็ตาม สมบัติเฟอร์โรอิเล็กทริก และแม่เหล็กที่เหมาะสมนั้นสามารถตรวจสอบได้ที่ปริมาณการเติมร้อยละ 0.1 โดยปริมาตรของการเติมโอบอลต์ และนิกเกิล